

FGF CARBON-P

CARBON-P is our 15% carbon fiber reinforced PET-G based material. The result is a more than twice as stiff filament as PET-G with increased impact and heat resistance. This, together with other features, such as a matt surface, no warp, dimensionally stable and extremely forgiving to print, makes CARBON-P suitable for a very wide variety of applications.

Material features:

- 15% Carbon fiber reinforced PET-G
- Extremely stiff
- Increased impact
- No warping and dimensionally stable
- Matt surface
- Abrasive (see * at additional info*)



Colours:

Colours on request. Ask your accountmanager.

Packaging:

FGF CARBON-P is available in 20kg bag

Processing recommendations

Drying	6hr,70°C. <200ppm
Zone 1 Temperature	220±20 °C
Zone 2 Temperature	245±20 °C
Zone 3 Temperature	220±20 °C
Mass temperature	218 °C
Die temperature	220±20 °C

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,31 g/cc
MFR 200°C/5 kg	ISO 1133	3,8 g/10min
Tensile Strength at Yield	ISO 527	101 Mpa
Tensile Strength at Break	ISO 527	100 Mpa
Elongation-Strain at Yield	ISO 527	2,7%
Elongation-Strain at Break	ISO 527	3,7%
Tensile modulus	ISO 527	9930 Mpa
Impact strength - Charpy notched 23°C	ISO 179	7 kJ/m2
Vicat softening temperature	ISO 306 B50	75 °C
Mold shrinkage	Internal method (ISO 294-4 based)	0,16%
Thermal expansion coefficient	ISO 11359	7,3*10 ⁻⁵ mm/mm°C

Additional info:

Due to virtually no warping of CARBON-P, this filament can also be printed without a heated bed. Please consider the use of a hardened steel nozzle and, if used, a gear pump, when printing with CARBON-P. The carbon fibers are abrasive and will result in fast wear of brass nozzles.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.

The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application.