

FGF Light Wood

FGF Light Wood is a modified PLA based granule, that smells and feels like wood. Light Wood is easy to print at a low temperature.

Material features:

- Feels and smells like wood
- Easy to print at low temperature
- Very low warping

Colours:

Colours on request. Ask your accountmanager.

Packaging:

FGF Light Wood is available in 20kg bag



Processing recommendations

Drying	8hr, 50°C*. <250ppm
Zone 1 Temperature	160±20 °C
Zone 2 Temperature	180±20 °C
Zone 3 Temperature	200±20 °C
Mass temperature	181 °C
Die temperature	205±20 °C

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,2 g/cc
MFR 200°C/5 kg	ISO 1133	5 g/10min
Tensile Strength at Yield	ISO 527	37 Mpa
Tensile Strength at Break	ISO 527	37 Mpa
Elongation-Strain at Yield	ISO 527	2%
Elongation-Strain at Break	ISO 527	2%
Tensile modulus	ISO 527	4180 Mpa
Impact strength - Charpy notched 23°C	ISO 179	7 kJ/m2
Vicat softening temperature	ISO 306	N/A
Mold shrinkage	Internal method (ISO 294-4 based)	N/A

Additional info:

*As PLA materials crystallize, it is advised to either have an agitated dryer, or dry at a lower temperature for a longer period. This avoids that the pellets stick to each other during drying. Avoid prolonged residence time in the extruder, as this can degrade the resin in the fibres.

Storage: Cool and dry (15-25 °C) and away from UV light. This enhances the shelf life significantly.

The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application.