

FGF PLA Bronze

FGF PLA Bronze is filled with 80% bronze. With FGF PLA Bronze you can create the most beautiful objects with real METAL characteristics, such as a 3 x higher weight than PLA, a METAL feel & touch and thermal-conductivity. Due to the high percentage of fillers FGF PLA Bronze has virtually no shrinkage.

Material features:

- Approx. 80% bronze content
- PLA-based, 3 times heavier
- Metal feel & “cold” touch
- Quick & easy polishing and other post-processing



Packaging:

FGF PLA Bronze is available in 20kg bag

Processing recommendations

Drying		8hr, 50°C*. <200ppm
Zone 1 Temperature		150±20 °C
Zone 2 Temperature		150±20 °C
Zone 3 Temperature		150±20 °C
Mass temperature		172 °C
Die temperature		165±20 °C

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	3,39 g/cc
MFR	ISO 1133	N/A
Tensile Strength at Yield	ISO 527	20,3 Mpa
Tensile Strength at Break	ISO 527	16,2 Mpa
Elongation-Strain at Yield	ISO 527	1%
Elongation-Strain at Break	ISO 527	3,5%
Tensile modulus	ISO 527	3930 Mpa
Impact strength - Charpy notched 23°C	ISO 179	3 kJ/m2
Vicat softening temperature	ISO 306 B50	N/A
Mold shrinkage	Internal method (ISO 294-4 based)	0,06%

Additional info:

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.

* Please consider the use of a hardened steel nozzle when printing with MT-BRONZE .

The bronze powder inside makes the filament abrasive and will result in fast wear of regular brass nozzles.

The values presented in this publication are based on MCP's knowledge and experience and are intended for reference purposes only. While MCP has made every reasonable effort to ensure the accuracy of the information in this publication, MCP does not guarantee that it is error-free, nor does MCP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCP reserves the right to make any adjustments to the information contained herein at any time without notice. MCP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCP shall not be liable for any damage, injury or loss induced from the use of MCP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application.