

FGF PPL

PPL is our special purpose Polypropylene, being specifically developed for having a very low density. This makes it perfect for objects where weight is a key factor. The surface has a matte finish and is resistant to absorbing moisture. Together with the chemical resistance of PP, PPL has unique qualities that aren't found in any other material which makes it an ideal choice for special projects. Although PPL features less warping than regular PP, it is still prone to heat warping.

Material features:

- Very Low density
- Good chemical resistance
- Good adherence on PP plate
- Floats

Colours:

Colours on request. Ask your accountmanager.



Packaging:

FGF PPL is available in 12,5kg bag

Processing recommendations

Drying	3hr,60°C. <1000ppm
Zone 1 Temperature	170±20 °C
Zone 2 Temperature	180±20 °C
Zone 3 Temperature	180±20 °C
Mass temperature	185-193 °C
Die temperature	195±20 °C

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	0,75 g/cc
MFR 200°C/5 kg	ISO 1133	5,8 g/10min
Tensile Strength at Yield	ISO 527	15 Mpa
Tensile Strength at Break	ISO 527	13,5 Mpa
Elongation-Strain at Yield	ISO 527	10%
Elongation-Strain at Break	ISO 527	30%
Tensile modulus	ISO 527	775 Mpa
Impact strength - Charpy notched 23°C	ISO 179	4,3 kJ/m2
Vicat softening temperature	ISO 306 B50	80,3°C
Mold shrinkage	internal method (ISO 294-4 based)	N/A

Additional info:

When PPL prints too "grainy", try purging the nozzle. Using a Gear pump or using high shear can affect the density of the material. Although drying is not necessarily required, it is advised to dry slightly.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.

The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application.